L Number	Hits	Search Text	DB	Time stamp
1	2	(linear adj expansion adj coefficient) and 349/5	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/28 08:30
2	87	(linear adj expansion adj coefficient) and substrate and diffract$4	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/28 08:33
-	1716	349/96	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:45
-	509	349/9	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:45
-	848	359/494	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:45
-	89	359/325	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:45
-	206	359/288	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:46
-	1198	(diffract$4 with thick$)and polariz$6	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:50
-	2	((diffract$4 with thick$)same isotropic)and polariz$6 and (anisotropic adj birefringent)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 10:58
-	2	((diffract$4 with thick$)same isotropic)and polariz$6 and (anisotropic with birefringent)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 11:01
-	5	((diffract$4 with thick$)same isotropic)and polariz$6 and anisotropic and birefringent	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 11:10
-	15	(diffract$4 with thick$)and isotropic and polariz$6 and anisotropic and birefringent	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:50
-	2	("5687153" | "6020944").PN.	USPAT	2003/05/26 12:50
-	0	(diffract$4 with thick$)and isotropic and polariz$6 and anisotropic and birefringent and 349/96	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:17
-	0	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and 359/325	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:31

-	2	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and minolta.as.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:51
-	1	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and 359/288	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:37
-	21	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and 359/494	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:38
-	4	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and 349/9	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:45
-	6	(diffract$4 and thick$)and isotropic and polariz$6 and anisotropic and birefringent and 349/96	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:46
-	3	(diffract$4 with thick$)and isotropic and polariz$6 and anisotropic and birefringent and 349/201	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:46
-	45419	minolta.as.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:50
-	24	birefringent and minolta.as.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/26 13:51
-	0	diffractive near (thermoplastic adj resin)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 09:52
-	1	diffract$4 near (thermoplastic adj resin)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 09:52
-	36439	diffract$4 and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:16
-	1947	diffract$4 and isotropic and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:16
-	473	diffract$4 and isotropic and mm and grat$4	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:17
-	13	349/201 and 349/202 and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 15:38

-	50	349/201 and 349/202	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:20
-	67	349/201 and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:40
-	203	diffract$4 and isotropic and mm and grat$4 and anisotropic	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:41
-	643	349/201	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 14:47
-	13	349/201 and 349/202 and mm	USPAT; US-PGPUB	2003/05/27 15:39
-	202	349/201 or 349/202 and mm	USPAT; US-PGPUB	2003/05/27 18:19
-	695	(349/201 or 349/202)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 15:40
-	83	(349/201 or 349/202) and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 16:34
-	5216	(diffract$4 with grating)and polariz$4	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 16:35
-	2107	(diffract$4 with grating)and polariz$4 and mm	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 16:35
-	0	(diffract$4 with grating)and polariz$4 and mm and 349/$.202-202	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 16:36
-	0	mm and 349/$.202-202	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/27 16:36
-	5158	linear adj expansion adj coefficient	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/28 08:30
-	8	(linear adj expansion adj coefficient) same substrate same diffract$4	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2003/05/28 08:33